

**Product Description**

- **Dimensions** 1200 L x 600 W x 3 TH (mm)
- **Packaging** 1 panel per package = 0,72 m<sup>2</sup> (3,2 kg )  
40 packs / pallet = 28,8 m<sup>2</sup> (116 kg)
- **Composition** Compact high pressure laminate (HPL), with decorative paper on top. Papers impregnated with melamine & phenol resins.
- **Edge sealing** Edges and joints to be sealed with construction adhesive Tec7 (or a similar MS-polymer adhesive and sealant).
- **Installation** To be glued to the substructure according to installation instructions. see box inlay or [www.berryalloc.com](http://www.berryalloc.com)

**General requirements**

Characteristics	Test standard	Units	Requirement	Typical values
Thickness of the element, t	EN 324-1	mm	± 0,2	± 0,1
Length of the surface layer, l	EN 324-1	mm	± 1,0	± 0,5
Width of the surface layer, w	EN 324-1	mm	± 1,0	± 0,5
Squareness of the element, q	Diagonal variance	mm	≤ 0,3	≤ 0,1
Openings between elements, o	EN 13329	mm	-	not available
Dimensional variations after changes in relative humidity	EN 318	mm	-	not available
Light fastness	EN 20105	Grade scale	Grey scale : ≥ 4	> 4
	EN ISO 105	Grade scale	Blue wool scale: ≥ 6	> 6
Surface hardness	NT Build 059	mm	-	not available
Impact resistance	NT Build 066	m	-	not available
Resistance to staining	EN 438.2.26	Rating <sup>1)</sup>	Group 1 & 2: 5 Group 3 & 4: 4	5 5

<sup>1)</sup> = Rating scale 1 to 5, where 5 is the best = "No visible change".

**Other technical data**

Characteristics	Test standard	Units	Requirement	Typical values
Formaldehyde, emission	EN 717-2	mg/m <sup>2</sup> * h	-	E1
Scratch resistance	EN 438.2.25	Rating <sup>1)</sup>	-	1
Fire behaviour	EN 13501-1	Class	-	C-s1, d0
Grout line deviation	-	mm	≤ 0,3	< 0,2

<sup>1)</sup> = Rating scale 1 to 5, where 5 is the best = "No visible change".

**Warranty and maintenance**

- **Residential warranty** Lifetime
- **Warranty conditions** see [www.berryalloc.com](http://www.berryalloc.com)
- **Care and maintenance** see [www.berryalloc.com](http://www.berryalloc.com)

